

Serial No. 09/761,317
October 14, 2003
Reply to the Office Action dated July 16, 2003
Page 2 of 11

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

Claim 1 (currently amended): A method of wiring formation comprising the steps of:

- forming a feeder film partially on a substrate;
- forming on the substrate a plating base film such that the plating base film partially overlaps the feeder film;
- forming a plated wiring on the plating base film; and
- selectively removing at least a portion of the feeder film that is exposed from the plated wiring; ~~wherein~~
~~the plating base film includes a diffusion preventive layer.~~

Claim 2 (original): A method of wiring formation according to Claim 1, wherein the step of forming on the substrate a plating base film is performed using a physical film making process.

Claim 3 (original): A method of wiring formation according to Claim 1, wherein the step of forming a plated wiring on the plating base film is performed using an electrolytic plating process.

Claim 4 (original): A method of wiring formation according to Claim 1, wherein the step of selectively removing at least a portion of the feeder film that is exposed from the plated wiring is performed using a wet etching process.

Serial No. 09/761,317
October 14, 2003
Reply to the Office Action dated July 16, 2003
Page 3 of 11

Claim 5 (original): A method of wiring formation according to Claim 1, wherein a width of a portion of the plating base film that is stacked on the feeder film is wider than the smallest wire width of the feeder film.

Claim 6 (original): A method of wiring formation according to Claim 1, wherein the plating base film comprises at least one of an adhesive layer and a diffusion preventive layer.

Claim 7 (currently amended): A method of wiring formation comprising the steps of:

- forming a feeder film partially on a substrate;
- forming on the substrate a resist pattern which has an opening defining a wiring forming area, such that a portion of the feeder film is exposed from the opening in the resist pattern;
- forming a plating base film at least on the substrate in the opening;
- forming a plated wiring on the plating base film in the opening;
- removing the resist pattern; and
- selectively removing at least a portion of the feeder film that is exposed from the plated wiring; wherein

~~the plating base film includes a diffusion preventive layer.~~

Claim 8 (original): A method of wiring formation according to Claim 7, wherein the step of forming on the substrate a plating base film is performed using a physical film making process.

Claim 9 (original): A method of wiring formation according to Claim 7, wherein the step of forming a plated wiring on the plating base film is performed using an electrolytic plating process.

Serial No. 09/761,317
October 14, 2003
Reply to the Office Action dated July 16, 2003
Page 4 of 11

Claim 10 (original): A method of wiring formation according to Claim 7, wherein the step of selectively removing at least a portion of the feeder film that is exposed from the plated wiring is performed using a wet etching process.

Claim 11 (original): A method of wiring formation according to Claim 7, wherein a width of a portion of the plating base film that is stacked on the feeder film is wider than the smallest wire width of the feeder film.

Claim 12 (original): A method of wiring formation according to Claim 7, wherein the plating base film comprises at least one of an adhesive layer and a diffusion preventive layer.

Claim 13 (previously presented): A method of manufacturing an electronic component comprising the steps of:

- providing a substrate;
- forming a feeder film partially on the substrate;
- forming on the substrate a plating base film by using a physical film making process such that the plating base film partially overlaps the feeder film;
- forming a plated wiring on the plating base film using an electrolytic plating process; and
- selectively removing at least a portion of the feeder film that is exposed from the plated wiring, using a wet etching process; wherein

the plating base film includes a diffusion preventive layer.

Claim 14 (original): A method according to Claim 13, wherein a width of a portion of the plating base film that is stacked on the feeder film is wider than the smallest wire width of the feeder film.

Serial No. 09/761,317
October 14, 2003
Reply to the Office Action dated July 16, 2003
Page 5 of 11

Claim 15 (previously presented): A method according to Claim 16, wherein a width of a portion of the plating base film that is stacked on the feeder film is wider than the smallest wire width of the feeder film.

Claim 16 (original): A method according to Claim 13, wherein the plating base film comprises at least one of an adhesive layer and a diffusion preventive layer.

Claim 17 (previously presented): A method of manufacturing an electronic component comprising the steps of:

- providing a substrate;
 - forming a feeder film partially on a substrate;
 - forming on the substrate a resist pattern which has an opening defining a wiring forming area, such that a portion of the feeder film is exposed from the opening in the resist pattern;
 - forming a plating base film at least on the substrate in the opening using a physical film making process;
 - forming a plated wiring on the plating base film in the opening using an electrolytic plating process;
 - removing the resist pattern; and
 - selectively removing at least a portion of the feeder film that is exposed from the plated wiring, using a wet etching; wherein
- the plating base film includes a diffusion preventive layer.

Claim 18 (original): A method according to Claim 17, wherein a width of a portion of the plating base film that is stacked on the feeder film is wider than the smallest wire width of the feeder film.

Serial No. 09/761,317
October 14, 2003
Reply to the Office Action dated July 16, 2003
Page 6 of 11

Claim 19 (previously presented): A method according to Claim 20, wherein a width of a portion of the plating base film that is stacked on the feeder film is wider than the smallest wire width of the feeder film.

Claim 20 (original): A method according to Claim 17, wherein the plating base film comprises at least one of an adhesive layer and a diffusion preventive layer.

Claim 21-24 (canceled).

Claim 25 (previously presented): A method according to Claim 1, further comprising a step of forming on the substrate a resist pattern having a reversed [taped] shape.

Claim 26 (previously presented): A method according to Claim 1, wherein the plating base film comprises an adhesive layer.